

## Jotashield Decor Antique Tex

**Substrate:** Plaster/CMU/Concrete

### Primer Coat

One coat: Jotashield Penetrating Primer or Jotashield Water Based Penetrating Primer:

Vol. solids: 34±2 %

### Texture Coats

Two coats: Jotashield Decor Antique Tex

Vol. solids: 62±2 %

### Properties

- **VOC content**  
50 g/l (ISO 11890 EU)
- **Determination of Carbon Dioxide**  
Equivalent Air Layer Thickness: R value- 234m  
Equivalent of 400mm concrete: Sc Value -59cm
- **Determination of Moisture Resistance**  
Equivalent Air Layer Thickness: 0.6m (avg)

### Glaze Coat (Optional for a two tone effect)

One coat: Jotashield Decor Glaze

Vol. Solids: 34±2 %

- Properties are for the top coat only tested with Jotashield Penetrating Primer unless otherwise mentioned.
- When more than one result is presented one star\* identifies the product being tested with Jotashield Alkali Resistant Primer and two stars\*\* identify that the product is tested with Jotashield Penetrating primer.