

Fenomastic Stain Resistant Emulsion Silk

Surface: Plaster/CMU/Concrete/Gypsum Board Partition

Primer Coat

One coat: Jotun Fenomastic Emulsion Primer:

Vol. solids: 25±2 %

Filler Coat

Two coats: Jotun Stucco:

Vol. solids: 50% ±2 %

Topcoats

Two coats: Jotun Fenomastic Stain Resistant

Vol. solids: 42±2 %

Properties

- **VOC content**
12.43 g/l (US EPA 24)
- **Washability/Scrub Resistance**
>20,000 scrubs (DIN 53778)
- **Hazardous Materials**
Free from:
 - Heavy Metals (ICP-AES)
 - APEO (BS 3762:90)
 - Formaldehyde (UV Spectroscopy)
 - Pthalates (GCMS)
- **Polish Resistance**
Gloss Change:
60° = 0.4 units
85° = 6.4 units
- **Stain Penetration**
Rating = 0, No penetration observed (0 = Best & 2 = Worst)
- **Easy Clean**
Rating: 0-1 (ASTM D 4828:94) (0 = All stains removed & 2 = No stains removed)